Fast Grass 40





PROPERTY DESCRIPTION AT740 Primary/Stalk Yarn Polymer 52% Polyethylene

Primary/Stalk Yarn Polymer 52% Polyethylene
Secondary/Thatch Yarn Polymer 48% Nylon

Yarn Cross Section Polyethylene Slit-Film/Texturized Nylon

Standard Colors

Field Green, White, Red, FLA Blue, Yellow, Black

UV Stabilized Yes

Fabric Construction Tufted

Primary Backing Dual layered woven polypropylene

Coating Type(s)

SilverBack™ Polyurethane or
5mm Polyurethane Foam w/fleece

Perforations Custom only


Polyethylene (Slit-Film) Yarn Denier/Ends 5040/1


Texturized Nylon Denier/Ends(Thatch) 4400/8

Recommended Infill N/A

Pile Height 3/4"

Pile Weight 40 oz.






THRESHOLD

Standard Line and Field Colors*

APPLICATION



















TESTING

FAST GRASS

FINISHED FABRIC	ENGLISH	SYSTEM	METRIC	SYSTEM	ASTM TEST F-1551
Nominal Specification	Value	Units	Value	Units	Method
Pile Height (Nominal)	3/4	ln.	19.05	mm.	D-5823
Face Weight	40	oz/yd²	1356	g/m²	D-5828
Total Fabric Weight (5mm Foam)	125	oz/yd²	4238	g/m²	D-5828
Total Fabric Weight (SilverBack™)	67	oz/yd²	2271	g/m²	D-5828
Primary backing Weight	7	oz/yd²	237	g/m²	D-5828
Secondary Coating Weight (Foam)	78	oz/yd²	2645	g/m²	D-5828
Secondary Coating Weight (SilverBack	(™) 20	oz/yd²	678	g/m²	D-5828
Tuft Bind	>8	lbs.	>3.6	Kg.	D-1335
Grab Tear Strength (Average)	>200	lbs.	>91	Kg.	D-2256
Lead Content	<50	ppm	<50	ppm	D-2766
Total Yarn Linear Density	9,400	Denier	10,445	D-Tex	D-1577
Tensile Strength	8.0	lbs.	3.63	Kg.	D-5034
Stitch Rate	13.5	Per 3"	17.68	Per 10 cm	D-5793
Machine Gauge	1/4	ln.	0.95	Cm.	D-5793
Flammability	TEST	PASSED	TEST	PASSED	D-2859
Water Permeability w/infill	>30	In./Hr.	>76	Cm./Hr.	F-1551
Fiber Thickness	9.4	mils	100	microns	D-3218
Fabric Width	12 & 15	Ft.	3.6 & 4.6	М	None

